

ENNIS ROADPLAST PROFILE

Product Specification

Product Code: CAP Px (depending on colour)

Ennis Roadplast Profile is a special grade of two-component cold-curing Methacrylate-based roadmarking compound. It is formulated from Roadplast resin with the distinct thixotropic property which allows the material, when correctly used, the capability to form raised ribs / blocks with or without base line. These raised rib / block formations provide the safety feature of providing an audio-tactile warning to drivers straying out of their lane.

Excellent durability and wear properties can be expected from *Ennis Roadplast Profile* because it is made from a tough, flexible acrylic polymer with best quality pigments.

Ennis Roadplast Profile is utilized mostly in white for delineation but other colours are also available.

Surface Preparation

The condition of the road surface is important if maximum service life is to be expected from *Ennis Roadplast Profile*. The road surface to be installed must be dry and free of any grease, oil, dirt, gravel, flaking pavement materials and any loose foreign materials. The temperature of the pavement surface should ideally be above 10°C. If the surface has been previously marked or treated (such as the application of curing compound on concrete) then a compatibility check should be carried out to establish if any surface preparation is necessary.

The following points require special consideration:

- New bituminous surfaces should be allowed to age for at least 4 weeks
- Concrete surfaces should be primed with *Ennis Roadplast Primer P1* (Product Code: MCAP1)
- Do not coat over thermoplastic marking
- Check compatibility over any previous markings

Application

Ennis Roadplast Profile can only be applied with a special machine with profile shoe features capable of operating pneumatic or electric valve to produce pre-set raised ribs/blocks heights at 25cm and 50cm centres with or without base line.

Ennis Roadplast Profile requires the thorough incorporation of a powdered initiator, *Dibenzoyl Peroxide* (Product Code: MCAP2). The amount of *Dibenzoyl Peroxide* powder added will vary between 0.5% and 3.0% by weight of *Ennis Roadplast Profile* depending on material temperature and road surface temperature (Consult the table at the end of this application section for the amount of *Dibenzoyl Peroxide* required).

If temperature of the *Ennis Roadplast Profile* material and road surface are similar then the pot life will be approximately be half the curing time of the marking.

Dibenzoyl Peroxide Powder Addition

The recommended amount of the *Dibenzoyl Peroxide* powder to be added to the *Ennis Roadplast Profile* base or top coat is between 0.5 and 3.0 percent by weight.

The table below is a guide to the amount of the *Dibenzoyl Peroxide* powder addition required by indicating how the pot life and curing time of the *Ennis Roadplast Profile* base and top coat is affected by the temperature and the amount of *Dibenzoyl Peroxide* powder added.

ENNIS COLD APPLIED PLASTIC

<i>Temperature (°C)</i>	<i>Hardener (% by Weight)</i>	<i>Pot Life (Mins)</i>	<i>Curing Time (Mins)</i>
10>	3.0	15	55
20>	1.5	10	45
30>	0.7	15	40

Transport and Storage

Refer to product Material Safety Data Sheet (MSDS).

Packaging

25kg (~16L) pail

Additional Information

Please contact Ennis Traffic Safety Solutions Pty Ltd if you require:

- An MSDS
- Pricing and availability
- Or more specific information on this product or other products in the wide range of products manufactured by Ennis Traffic Safety Solutions specifically for the roadmarking industry.

Ennis Traffic Safety Solutions Pty Ltd

29-31 Memorial Avenue

Ingleburn NSW 2565

Tel: 02 9829 4275 Fax: 02 9829 4362

Email: Enquiry@ennistraffic.com.au

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the preceding is made in lieu of all warranties, expressed or implied.