



GT EXTRUSION THERMOPLASTIC YELLOW

Product Specification

Product Code: TEX2

GT Extrusion Thermoplastic Yellow is a long life roadmarking material manufactured to conform to RTA 3357 and AS 4049.2 standards. It is extruded under pressure through a slit of predetermined size, resulting in a line of constant width and thickness.

Physical Characteristics

| | |
|---|-----------------|
| Colour | : yellow |
| Luminance | : 50 minimum |
| Softening Point (°C) | : 90 minimum |
| % Loss (L/F) | : 5 maximum |
| Skid Resistance (BPN) | : 55 minimum |
| Flow Resistance (%) | : 10 maximum |
| Gradation of Mineral Content (RTA T855) | : pass |
| Glass Beads Content (%w/w) | : 20 minimum |
| Abrasion Resistance (g/100rev) | : 0.6g maximum |
| Flash Point (°C) | : 230°C minimum |
| Density (g/cm ³) | : 1.9 – 2.0 |

Application

Application of *GT Extrusion Thermoplastic Yellow* requires the skills of trained personnel and specialised equipment. It is applied by a truck-mounted or self-propelled pressurised vessel or auger fed extruder. The material is heated to an application temperature of 180°C to 200°C with a maximum temperature of 230°C.

Transport

GT Extrusion Thermoplastic Yellow is not classed as dangerous goods by the Australian Code for the Transport of Dangerous Goods by Road or Rail (ADG Code).

Storage

Store under cover in a cool area, protected from moisture. Stock should be rotated and used within 6 months of the date of manufacture.

Additional Information

Please contact GT Industries Pty Ltd if you require:

- A Material Safety Data Sheet
- Pricing and availability
- Or more specific information on this product or other products in the wide range of products manufactured by GT Industries specifically for the roadmarking industry.

GT Industries Pty Ltd

1/29-31 Memorial Avenue

Ingleburn NSW 2565

Tel: 02 9829 4275 Fax: 02 9829 4362

Email: gtind@ozemail.com.au

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the preceding is made in lieu of all warranties, expressed or implied.